## **AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

- 1. (Original) A method of treating a process stream by catalysis, comprising passing the process stream through a chemical reactor containing catalytic material and including the step of passing the process stream through a layer of filter material located in the reactor, the layer comprising shaped porous bodies of ceramic material, the porosity being from about 65% to about 90%, the pores being defined by struts and walls in at least some of which windows are formed to allow fluid communication between adjacent pores.
- 2. (Original) A method according to Claim 1, wherein the pore size of the pores in the porous bodies ranges from about 50 micron to about 1500 micron.
- 3. (Currently Amended) A method according to Claim 1-or 2, wherein the window size is less than 450  $\mu m$ .
- 4. (Currently Amended) A method according to Claim 1, <del>2 or 3,</del> wherein the porosity of the porous bodies exceeds 75% so that the pores are all interconnected.

National Stage of PCT/GB2004/001271 Attorney Docket No. S1011/20206 Preliminary Amendment Dated August 18, 2006

- 5. (Currently Amended) A method according to any preceding Claim 1, wherein the density of the body ranges from about 10% to about 30% of theoretical density.
- 6. (Currently Amended) A method according to any preceding-Claim\_1, wherein the pore surfaces of the bodies are coated with catalytic species prior to use.
- 7. (Currently Amended) A method according to any preceding Claim 1, wherein the filter material is held in a rotating wheel or slide configuration such that only a proportion of the filter material is exposed to the process stream at any one time and the other portions of the filter are exposed to a regenerative process or being held in a standby mode.
- 8. (Original) A method of fabricating chemical reactor filter material, the material comprising porous bodies having a porosity of from 65 to 95%, the method comprising the steps of:
  - a) forming a dispersion comprising particles in a liquid carrier and a binder;
  - b) introducing gas into the dispersion; and
  - c) removing the liquid carrier to provide a solid article having pores derived from the bubbles,

wherein the dispersion has a critical viscosity selected to be below the level at which the introduction of gas cannot take place and above the level at which entrapped gas bubbles will tend to escape.

National Stage of PCT/GB2004/001271 Attorney Docket No. S1011/20206 Preliminary Amendment Dated August 18, 2006

- 9. (Original) A method according to Claim 8, wherein the critical viscosity of the dispersion is in the range of from about 5 mPa.s, to about 1000 mPa.s.
- 10. (Currently Amended) A method according to Claim 8-or-9, wherein the critical viscosity of the dispersion is in the range from about 25 mPa.s to about 1000 mPa.s.
- 11. (Currently Amended) A chemical reactor (10) comprising a filter material (100)-formed in accordance with the method of any of Claims 8-to 10.
- 12. (Currently Amended) A chemical reactor filter material—(100), comprising a plurality of shaped porous bodies, each body having a porosity of from 65 to 95% and comprising struts—(1) and walls—(2), at least some of the walls—(2) having windows—(3) therein to allow fluid communication between adjacent pores—(4).
- 13. (Currently Amended) A filter material (100) according to Claim 12, wherein the window size is less than 450 μm.
- 14. (Currently Amended) A filter material—(100) according to Claim 11,—12 or 13, wherein at least some of the surface of at least some of the porous bodies are coated with one or more catalysts.

National Stage of PCT/GB2004/001271 Attorney Docket No. S1011/20206 Preliminary Amendment Dated August 18, 2006

- 15. (Currently Amended) A filter material-(100) according to Claim 14, wherein the catalyst is photolytically activated or activatable.
- 16. (New) A filter material according to Claim 12, wherein at least some of the surface of at least some of the porous bodies are coated with one or more catalysts.
- 17. (New) A filter material according to Claim 16, wherein the catalyst is photolytically activated or activatable.